Valley Lelux 700

Description : Valley Lelux 700 is an air drying matt enamel suitable for all applications over metal, wood and walls.

Technical Data :

Viscosity	23-25 sec / ford cup 8
Solid Content	70-77 %
Density	1.40-1.55 gm/cm3
Coverage	6-8 m^2/kg (Dry film thickness 50-60 µ)

Substrates and surface preparation : Valley Lelux 700 is recommended for application over wood, metal and walls after proper priming. All new or already painted surfaces should be free from dust, grease and waxes.

Application : Apply Valley Lelux 700 after dilution with white spirit from (10%-30%) to reach the suitable application viscosity.

Drying time at 25 °C & 60% R.H :
Initial drying time 2-3h
Recoating time 8h
Final drying time 16h

Tools : Spray gun, brush or roller

Color : White and colored according to Valley color guide

Expiry : Two years from production date if stored in original sealed container at normal temperature. Keep away from direct sun light.