Valley Lelux 800

Description : Valley Lelux 800 is an air drying gloss enamel suitable for all applications over metal, wood and walls.

Technical Data :

Viscosity	25-45 sec / ford cup 8
Solid Content	57-69 %
Density	0.93-1.20 gm/cm3
Coverage	10-12 m2/kg (Dry film thickness 40-50 µ)

Substrates and surface preparation : Valley Lelux 800 is recommended for application over wood, metal and walls after proper priming. All new or already painted surfaces should be free from dust, grease and waxes.

Application : Apply Valley Lelux 800 after dilution with white spirit from (10%-30%) to reach the suitable application viscosity.

Drying time at 25 °C & 60% R.H :
Initial drying time 3-4h
Recoating time 24h
Final drying time 24h

Tools : Spray gun, brush or roller

Color : White and colored according to Valley color guide

Expiry : Two years from production date if stored in original sealed container at normal temperature. Keep away from direct sun light.